

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 04-239540

(43)Date of publication of application : 27.08.1992

(51)Int.Cl.

C08J 9/00
 B29C 55/12
 B32B 5/18
 B32B 27/36
 C08L 23/20
 C08L 67/02
 G09F 9/30
 H04N 5/74
 // B29K 67:00
 B29L 7:00
 C08L 67:02

(21)Application number : 03-020328

(71)Applicant : TORAY IND INC

(22)Date of filing : 22.01.1991


(72)Inventor : MIYAGAWA KATSUTOSHI
 TSUNASHIMA KENJI
 AOKI SEIZO

(54) WHITE POLYESTER FILM

(57)Abstract:

PURPOSE: To obtain a white polyester film capable of obtaining brighter screen having higher percentage of reflectance when used as a substrate for liquid crystal display reflecting sheet and optimum as the substrate for liquid crystal display reflecting sheet.

CONSTITUTION: The objective white polyester film in which average percentage of reflectance in wavelength area of light of 400-700nm on the surface is $\geq 90\%$ and (maximum value - minimum value) of percentage of reflectance in the wavelength area is $\leq 10\%$ and the objective white polyester film in which average percentage of reflectance in wavelength area of light of 330-380nm on the surface is $\geq 90\%$.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision
of rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office